

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 18/70, 18/80	A1	(11) International Publication Number: WO 97/12924 (43) International Publication Date: 10 April 1997 (10.04.97)
(21) International Application Number: PCT/GB96/02440 (22) International Filing Date: 4 October 1996 (04.10.96) (30) Priority Data: 9520317.0 5 October 1995 (05.10.95) GB (71) Applicant (for all designated States except US): BAXENDEN CHEMICALS LIMITED [GB/GB]; Paragon Works, Baxenden, Near Accrington, Lancashire BB5 2SL (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): RIMMER, Ian, Kevin [GB/GB]; Baxenden Chemicals Limited, Paragon Works, Baxenden, Near Accrington, Lancashire BB5 2SL (GB). SPENCER, Richard, Alan [GB/GB]; Baxenden Chemicals Limited, Paragon Works, Baxenden, Near Accrington, Lancashire BB5 2SL (GB). (74) Agents: CRESSWELL, Thomas, Anthony et al.; J.A. Kemp & Co., 14 South Square, Gray's Inn, London WC1R 5LX (GB).		(81) Designated States: AU, BR, CA, CZ, HU, JP, KR, PL, RU, UA, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: WATER DISPERSIBLE BLOCKED ISOCYANATES (57) Abstract <p>A water dispersible blocked polyisocyanate of formula (I) $R-Y_m$, where R is an m valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group and comprising at least three consecutive ethylene oxide groups or at least one residue of a polyhydroxy carboxylic acid, and each group Y, which may be the same or different, is a group of formula (II), where each R^1 is the same or different when n is more than 1 and each R^1 is an alkyl, alkenyl, aralkyl, N-substituted carbamyl, phenyl, NO_2, halogen or a group $-C(O)-O-R^2$, where R^2 is hydrogen or an alkyl group; n is 0, 1, 2 or 3; and m is an integer of 2 or more.</p> <div style="display: flex; justify-content: space-around; align-items: center;"> <div data-bbox="876 1276 1274 1386"> </div> <div data-bbox="1396 1323 1445 1365"> (II) </div> </div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

- 1 -

WATER DISPERSIBLE BLOCKED ISOCYANATES

The present invention relates to water dispersible blocked polyisocyanates, methods for making them, water-based storage stable materials, and coatings
5 containing them.

Blocked polyisocyanates are commonly used in coatings, such as paints, which also contain active hydrogen containing compounds e.g. amines and alcohols. These coatings are deposited onto the article to be coated and
10 then subsequently hardened by heating, often referred to as stoving. During stoving the blocked polyisocyanates dissociate so that the isocyanate groups become available to react with the active hydrogen containing compounds. This leads to crosslinking and hardening of the coating.

15 A blocked polyisocyanate coating composition ideally has two properties: (a) a dissociation temperature low enough to allow hardening without heating to temperatures which degrade the coated item and (b) water dispersibility so that the use of organic solvents can be kept to a
20 minimum or eliminated. However, generally a blocked polyisocyanate having a low dissociation temperature will be highly reactive and thus will be inherently unstable in water so that the two properties are incompatible.

Various means for increasing water dispersibility have
25 been described.

US 4,522,851 describes a water-dispersible blocked isocyanate in which a hydrophilic group such as an anionic

- 2 -

group is chemically incorporated into the polyisocyanate component to make the blocked polyisocyanate water-dispersible. US-A-4,507,427 describes aqueous blocked polyisocyanate solutions or dispersions produced by mixing
5 the blocked polyisocyanate with water in the presence of enough base to guarantee the solubility or dispersibility of the polyisocyanates. US 4,098,933 describes water-dispersible blocked polyisocyanates in which the blocking groups contain a hydrophilic group such as a carboxylic
10 acid salt or polyethylene oxide units.

Most conventional blocked polyisocyanates dissociate at temperatures of around 160°C. EP-A-0159117 discloses pyrazole blocked polyisocyanates which dissociate at a temperature significantly lower than this. Since the
15 pyrazole blocked polyisocyanates are more reactive than conventional blocked isocyanates, they are inherently less stable.


The present inventors have now established that, despite their high reactivity, certain pyrazole blocked
20 polyisocyanates can be used in aqueous dispersion coating compositions and that the compositions have good storage stability. Accordingly the present invention provides a water dispersible blocked polyisocyanate of the formula (I)



25 where R is an m valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group and comprising at least three consecutive ethylene oxide groups

- 3 -

or at least one residue of a polyhydroxy carboxylic acid,
and each group Y, which may be the same or different,
is a group of formula (II)



where R¹ is an alkyl, alkenyl, aralkyl, N-substituted
10 carbamyl, phenyl, NO₂, halogen or a group -C(O)-O-R²
where R² is hydrogen or an alkyl group;

n is 1, 2 or 3; and

m is an integer of 2 or more.

Preferably m is an integer from 2 to 6, for example 2,
15 3, 4, 5 or 6. When n is 2 or 3, the groups R₁ may be the
same or different. When R-Y_m contains more than one group
-C(O)OR², the groups R² may be the same or different.

In addition the present invention provides a water
dispersible mixture of blocked polyisocyanates each of the
20 formula




where the groups R are the same or different and each is an
m valent group comprising an aliphatic, cycloaliphatic
heterocyclic or aromatic group and wherein from 5 to 100
25 eq.wt% (preferably from 10 to 100 eq.wt%) of groups R
comprise at least three consecutive ethylene oxide groups
or at least one residue of a polyhydroxy carboxylic acid,

- 4 -

and each group Y, which may be the same or different, is a group of formula (II) as defined above.

According to a further embodiment, the invention provides a water dispersible product obtainable by

5 (a) contacting a polyisocyanate of formula (III)



wherein R^a is a q valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group and q is an integer greater than 2,

10 with an active hydrogen-containing compound bearing a hydrophilic group which is $-(CH_2CH_2O)_p-$ where p is 3 or more or with a polyhydroxy carboxylic acid group or derivative thereof to form a water dispersible polyisocyanate of formula $R(NCO)_m$ where R is an m valent group comprising an
15 aliphatic, cycloaliphatic, heterocyclic or aromatic group comprising at least three consecutive ethylene oxide groups or a residue of a polyhydroxycarboxylic acid; and

(b) blocking the water dispersible polyisocyanate produced in step (a) with a pyrazole of formula (IV)

20



wherein R^1 and n are as defined in relation to formula (I) above.

25 A substance is considered to be water dispersible for the purposes of the present invention if it forms a dispersion in water which is uniform on a macroscopic scale

- 5 -

but consists of particles or droplets of the substance in water. Preferably the dispersion is a colloid, in which, for example, the particles or droplets of the dispersed substance have a diameter which is about the wavelength of light, for example about 500 nm. In general the particle or droplet is an aggregate of numerous molecules, but is too small to be seen with an optical microscope. The particles or droplets generally pass through most filter papers but can usually be detected by light-scattering, sedimentation and osmosis. Preferably the dispersion is an emulsion or sol of blocked polyisocyanate in water. An emulsion is generally a dispersion of liquid in liquid. A sol is generally a dispersion of a solid in a liquid.

An alkyl, alkenyl or aralkyl group may be a branched or straight chain group and may be substituted, for example with a halogen, such as fluorine, chlorine or bromine, or -OH. An alkyl group is preferably a C₁ to C₆ alkyl group, more preferably a C₁ to C₄ alkyl group, for example, methyl, ethyl, propyl, isopropyl, butyl, sec-butyl or tert-butyl. Most preferably it is methyl. An alkenyl group is preferably a C₂ to C₆ alkenyl group, for example C₂, C₃, C₄, C₅ or C₆ alkenyl. An aralkyl group preferably has substituted or unsubstituted phenyl as the aryl portion. The alkyl portion is generally an alkyl group as defined above.

A polyhydroxy carboxylic acid is a compound having 2 or more hydroxyl groups and one or more carboxylic acid

- 6 -

groups, such as dimethylolpropionic acid.

Preferably n is 2 or 3.

Preferably m is an integer from 2 to 6. More preferably m is 2 or 3.

5 A halogen is, for example chlorine, bromine or fluorine. Preferably it is chlorine or bromine.

An N-substituted carbamyl group is generally of formula $-C(O)NR^3R^4$, where R^3 and R^4 may be the same or different and each is hydrogen or an alkyl or alkenyl
10 group, provided that R^3 and R^4 are not both hydrogen.

According to one embodiment the group R in the blocked isocyanate of formula (I) comprises at least three consecutive ethylene oxide groups or at least one residue of a polyhydroxy carboxylic acid. According to a second
15 embodiment, from 5 to 100% by equivalent weight of groups R comprise at least three consecutive ethylene oxide groups or at least one residue of a polyhydroxycarboxylic acid.

Consecutive ethylene oxide groups are groups bonded directly together. Three consecutive ethylene oxide groups
20 can be represented as $-(CH_2CH_2O)_3-$. When R comprises consecutive ethylene oxide groups, it preferably comprises at least five, for example at least 7, 9 or 12 consecutive ethylene oxide groups. Preferably R comprises 0.01 to 25% by weight, based on the weight of the unblocked
25 polyisocyanate, of ethylene oxide units, more preferably 0.5 to 25% by weight. R may comprise further ethylene oxide groups which are not consecutive with or bonded

- 7 -


directly to the three consecutive ethylene oxide groups.

When R comprises residues of polyhydroxy carboxylic acid, it preferably comprises at least 2 residues, preferably at least 3, for example 5, 8, 12 or more
5 residues of polyhydroxy carboxylic acid. Preferably R comprises 0.01 to 25% by weight, based on the weight of the unblocked polyisocyanate of polyhydroxy carboxylic acid residues, more preferably 0.5 to 25% by weight.


R may comprise residues of polyhydroxy carboxylic acid
10 as well as at least three consecutive ethylene oxide groups. When less than 100 wt% of groups R comprise at least one residue of polyhydroxy carboxylic acid or at least three consecutive ethylene oxide groups, preferably at least 15 wt%, for example, at least 20, 30, 40, 50 or 60
15 wt% of groups R comprise at least one residue of polyhydroxy carboxylic acid or at least three consecutive ethylene oxide groups. When the polyhydroxy carboxylic acid is dimethylol propionic acid (DMPA) the ratio of isocyanate/hydroxyl groups is generally 0.05 to 0.7,
20 preferably 0.2 to 0.3 on an equivalent weight basis, so isocyanate is in excess.

Preferably at least one group Y is


- 8 -



5



10 More preferably at least one group Y is



15

The present invention provides a process for producing a water dispersible blocked polyisocyanate which process comprises contacting a polyisocyanate of formula R(NCO)_m with a blocking agent, where R and m are defined as for the blocked isocyanate of formula (I). Preferably the resulting blocked polyisocyanate contains no free isocyanate groups.

The present invention further provides a process which comprises (a) contacting a conventional polyisocyanate of formula (III) as defined above

with an active hydrogen-containing compound bearing a hydrophilic group which is $\text{—(CH}_2\text{CH}_2\text{O)}_p\text{—}$ where p is 3 or more

- 9 -

or a carboxylic acid group or derivative thereof to form a water dispersible polyisocyanate of formula $R(NCO)_m$; and

(b) blocking the water dispersible polyisocyanate produced in step (a) with a pyrazole of formula (IV) as defined above.

The blocking agents used in the present invention are pyrazoles of the formula (IV) as defined above.

Examples of suitable pyrazoles include

3,5-dimethylpyrazole, 3-methylpyrazole,
4-nitro-3,5-dimethylpyrazole and 4-bromo-3,5-dimethylpyrazole. The preferred blocking agent is 3,5-dimethylpyrazole.

The polyisocyanate of formula $R(NCO)_m$ which is to be blocked is a water dispersible organic polyisocyanate suitable for crosslinking compounds containing active hydrogen. Suitable polyisocyanates comprise, for example, aliphatic groups including cycloaliphatic, aromatic, heterocyclic, and mixed aliphatic aromatic groups. The polyisocyanates contain 2, 3 or more isocyanate groups.

The polyisocyanate of formula $R(NCO)_m$ may be, for example, selected from those described in US 4,522,851 or may be a polyisocyanate prepolymer obtained by reacting a conventional polyisocyanate, such as a diisocyanate, with a compound comprising at least three consecutive ethylene oxide units or at least one polyhydroxy carboxylic acid residue.

The conventional polyisocyanates are generally C_1 to

- 10 -


C₁₂ alkylene diisocyanates, or dimers or trimers thereof, aryl diisocyanates or cycloalkyl diisocyanates. The conventional polyisocyanates include, for example toluene diisocyanate, such as 2,4- and 2,6-toluene diisocyanate
5 ethylene diisocyanate and mixtures thereof, propylene diisocyanate, 4,4-diphenylmethane diisocyanate, p-phenylene diisocyanate, tetramethylene diisocyanate, hexamethylene diisocyanate, decamethylene diisocyanate, dodecamethylene diisocyanate, 2,4,4-trimethylhexamethylene-1,6
10 diisocyanate, phenylene diisocyanate, tolylene or naphthylene diisocyanate, 4,4'-methylene-bis(phenyl isocyanate), 4,4'-ethylene-bis(phenyl isocyanate), ω,ω' -diisocyanato-1,3-dimethyl benzene, ω,ω' -diisocyanato-1,4-dimethylcyclohexane, ω,ω' -diisocyanato-1,4-dimethyl
15 benzene, ω,ω' -diisocyanato-1,3-dimethylcyclohexane, 1-methyl-2,4-diisocyanatocyclohexane, 4,4'-methylene-bis(cyclohexyl isocyanate), 3-isocyanato-methyl-3,5,5-trimethylcyclohexyl isocyanate, dimer acid-diisocyanate, ω,ω' -diisocyanatodiethyl benzene, ω,ω' -diisocyanatodimethyl
20 toluene, ω,ω' -diisocyanatodiethyl toluene, fumaric acid bis(2-isocyanato ethyl) ester, triphenylmethane triisocyanate, 1,4-bis(2-isocyanato-prop-2-yl) benzene and 1,3-bis(2-isocyanato prop-2-yl) benzene.

Particularly preferred conventional polyisocyanates
25 are the biuret, uretdione or isocyanurate of a C₁ to C₁₂ alkylene diisocyanate, such as 1,6-hexamethylene diisocyanate (HMDI). The isocyanurate of HMDI is the

- 11 -

isocyanate "trimer" and has the structure


5



10

The uretdione of HMDI is the "dimer" and has the structure

15



The polyisocyanate prepolymers may be obtained by
 20 reaction of an excess amount of the conventional
 polyisocyanate with an active hydrogen containing compound,
 for example, a polyol or a polyamine, such as a lower
 molecular weight polyol or polyamine, for example having a
 molecular weight of 300 or less, or a medium molecular
 25 weight polyol or polyamine, for example a polyol or
 polyamine having a molecular weight of 300 to 8000.

In addition to the at least one residue of polyhydroxy

- 12 -

carboxylic acid or at least three consecutive ethylene oxide groups, the polyol or polyamine preferably comprises, for example, dimers, trimers or polymers of one or more of ethylene glycol, propylene glycol, 1,3-butylene glycol
 5 neopentyl glycol, 2,2,4-trimethyl-1,3-pentane diol, hexamethylene glycol, cyclohexane diethanol, hydrogenated bisphenol-A, trimethylol propane, trimethylol ethane, 1,2,6-hexane triol, glycerine, sorbitol or pentaerythritol.

Preferably the polyol or polyamine comprises residues
 10 of at least one of diethylene glycol, triethylene glycol or polyethylene glycol, preferably in an amount that the resulting unblocked polyisocyanate comprises 0.01 to 25% by weight of ethylene oxide units. Preferably the active hydrogen containing compound is a polyoxyalkylene amine
 15 such as Jeffamine M-1000.

The di- or polyisocyanate obtained by the above reaction may comprise a biuret group having the structure



or an allophanate group having the structure



The polyisocyanate may be cyclic, for example a derivative,

- 13 -

such as an ester, of isocyanuric acid.

Preferably the isocyanate group of the polyisocyanate is not bonded directly to an aromatic nucleus in the group R.

5 The reaction between the polyisocyanate $R(NCO)_m$ and the blocking group is exothermic. Since the reaction product will dissociate if the temperature is raised sufficiently, cooling may be required to keep the temperature of the reaction mixture down, preferably to
10 80°C or less. The resulting blocked polyisocyanate is then recovered and may be isolated or purified.

The present invention further provides an aqueous dispersion of at least one blocked isocyanate as defined herein. Surprisingly the aqueous dispersions are storage
15 stable for at least four months at room temperature whilst providing blocked polyisocyanates which dissociate at relatively low temperatures.

At 40°C these dispersions have been found to be storage stable for several weeks, and up to several months.
20 This has significant commercial benefit, allowing users in warm climates to take advantage of the low unblocking temperatures whilst retaining adequate storage stability.

The dispersions are formed by, for example, stirring or agitating a mixture of water and the blocked isocyanate.
25 Typically the dispersion is formed using an anchor stirrer at 250 to 300 rpm. It is also possible to use a high speed "Greaves" mixer to disperse the product.

- 14 -

The dispersions may additionally comprise at least one of an emulsifier, a detergent, a colourant, a pigment, a resin, a surfactant, a catalyst or an antioxidant.

Preferably the dispersions contain only water and blocked
5 isocyanate. Generally the dispersion comprises from 5 to 95% by weight, based on the weight of the dispersion, of blocked polyisocyanate, preferably 30 to 70%, more preferably 35 to 60% by weight of blocked polyisocyanates.

The present invention further provides a water-based
10 coating composition which comprises an aqueous dispersion as defined above and at least one compound containing an active hydrogen, selected from, for example, alcohols, amines, polyhydroxy-polyesters, polyhydroxy polyethers, polylactones, hydroxypolycarbonates, polythioethers,
15 polyacetals, polyether esters, polyester amides and polyamide-polyamine resins, e.g. the product from a dimer fatty acid and an aliphatic polyamide.

Preferably the compound containing an active hydrogen atom is an acrylic resin containing a carboxylic acid group
20 and hydroxy groups, a water dispersible polyester or polyether resin or a hydroxyacrylic resin containing a tertiary amine group, or polymers thereof.

Generally the coating composition comprises from 10 to 90% by weight based on the weight of the composition of the
25 compound containing an active hydrogen atom.

Typically the coating composition may comprise at least one of an emulsifier, a detergent, a colourant, a

- 15 -

pigment, a resin, a surfactant, a catalyst, an antioxidant, a dispersing aid, a fungicide, a viscosity modifier, a defoamer, a flow additive or a coalescing solvent.

The coating compositions of the present invention conveniently provide one component storage stable coating formulations, which are generally stable for at least four months at room temperature, that is at a temperature between 15 and 22°C, generally, 16, 17 or 18°C.

Typically a coating composition according to the invention will comprise components in the following proportions:

	<u>Component</u>	<u>Parts by weight</u>
	1) Water	8.0
	2) Dispersing Aid	0.3
15	3) Dimethylaminoethanol	0.6
	4) Fungicide	0.1
	5) Titanium Dioxide	18.0
	6) Viscosity Modifier	3.0
	7) Defoamer	0.3
20	8) Flow Additive	0.3
	9) Acrylic Emulsion (45% solids)	47.0
	10) Blocked Isocyanate	22.0
	11) Coalescing Solvent	0.4

25

According to a further embodiment of this invention, the coating is a paint composition comprising a pigment

- 16 -

carrier containing active hydrogen groups, a pigment and an aqueous dispersion of a compound of formula I.

These paints usually comprise a pigment dispersed in an aqueous dispersion of a pigment carrier. Preferably the pigment carrier is a resin containing an active hydrogen, which resin is to be crosslinked by the polyisocyanate. Preferably the paint contains 0.5 to 2 blocked isocyanate groups per active hydrogen containing group. Suitable active hydrogen containing resins include

polyamide-polyamine resins, e.g. the product from a dimer fatty acid and an aliphatic polyamide, carboxylic acid group containing acrylic resins, or tertiary amine group containing hydroxyacrylic resins and polymers thereof.

The total concentration of the dispersed solid will, of course, depend upon the process for which the paint is to be used. Various standard additives such as surface active agents, catalysts and anti-oxidants may also be incorporated.

The coatings according to the invention may be deposited electrophoretically or conventionally e.g. by spray depositing, dipping, applying with a roller or brush, transfer coating, screen painting, electrostatic spraying, using a doctor blade or electrocoating or by other means onto the articles to be coated and then subsequently hardened by heating the deposited coating to crosslink the compound containing an active hydrogen.

The electrophoretic deposition process is well known

- 17 -

and involves the use of a cathode and an anode in contact with a bath containing the paint. The surface to be coated is the surface of one of the electrodes. On applying a voltage of generally 1 to 3,000 volts across the electrodes
5 the paint is deposited onto the surface of one of the electrodes.

The coated article is removed from the bath and stoved e.g. baked in an oven. The blocking groups dissociate from the isocyanate groups, which then react with the compound
10 containing the active hydrogen. This results in crosslinking and hardening of the coating. Coating compositions according to this invention are generally hardened at temperatures from 100 to 180°C, for instance at up to 140°C or, preferably, up to 120°C.

15 The present invention further provides the use of an aqueous dispersion of a blocked isocyanate as defined herein as a coating composition, such as a paint.

Other uses of the aqueous dispersions and coating compositions of the invention include clear coatings
20 (similar to paints but lacking opaque pigments) and water based textile coatings and crosslinkers for fabrics. The low unblocking temperature permits the aqueous dispersions and coating compositions to be used to coat relative heat sensitive substrates such as plastics which would melt or
25 degrade at higher storing temperature. A preferred use of the aqueous dispersions and coating compositions is in the automotive industry, for instance in or as primers,

- 18 -

basecoats, topcoats and lacquers for automobiles.

The present invention further provides a coating process which comprises applying the coating to an item and heating it to achieve hardening of the coating.

5 The invention is illustrated by the following
Examples.

EXAMPLES

Example 1 - Production of aqueous dispersion of blocked
isocyanate.

The following reactants were used:

		<u>Weight %</u>
	1) 1,6-Hexamethylene diisocyanate trimer	30
15	2) Polyoxyalkylene amine (Jeffamine M-1000)	3
	3) 3,5-Dimethyl pyrazole (Blocking agent)	16
	4) Butyl glycol ether (solvent)	7
	5) Sodium sulphosuccinate (Disponil SUS 87)	4
	6) Water	40

20 (1) was added to a reaction vessel. (2) was slowly added to the reaction vessel. The vessel was heated to 60 to 70°C until an isocyanate content of 20 to 21 mol % was reached. The temperature was maintained at 60 to 70°C
25 while (3) was added slowly until an isocyanate content of zero was reached. (4) and (5) were added and mixed for 5 minutes. Water was added and a dispersion was formed using

- 19 -

a high speed mixer.

Jeffamine M-1000 is the active hydrogen-containing compound which reacts with the HMDI trimer to form a polyisocyanate prepolymer. Sodium sulphosuccinate is an ionic surfactant which helps to control the particle size of the dispersion.

Example 2 - Production of aqueous dispersion of blocked isocyanate

The following reactants were used:

		<u>Weight %</u>
10	1) 1,6 Hexamethylene diisocyanate trimer	26.7
	2) n-Methyl pyrrolidone	6.0
	3) Dimethyl pyrazole	11.3
	4) Dimethylol propionic acid	1.9
15	5) DMAMP 80 (Angus Chemie)	2.0
	6) Water	52.1

1) was added to a reaction vessel. (2) was added and the vessel heated to 60-70°C. The temperature was maintained at 60-70°C while (3) was added slowly until an isocyanate content of 2.8% was reached. (4) was added and the reaction continued until an isocyanate content of zero was reached. The batch was cooled to 60°C before adding (5) and (6).

- 20 -

Example 3 - Production of white paint composition.

	<u>Component</u>	<u>Parts by weight</u>
	1) Water	8.0
5	2) Dispersing aid (Dispex 40)	0.3
	3) Dimethylaminoethanol	0.6
	4) Fungicide (Acticide SPX)	0.1
	5) Titanium dioxide	18.0
	6) Viscosity modifier (Rheovis CR2)	3.0
10	7) Defoamer (Foamex 1488)	0.3
	8) Flow additive (Aerosol 0775)	0.3
	9) Acrylic emulsion (Xenacryl (45% solids) DP 9B/1283)	47.0
	10) Blocked isocyanate	22.0
15	11) Coalescing solvent (Ectrapro EEP)	0.4

Components (1), (2), (4), (5), (7), 0.06 parts by weight of component (3) and 1.5 parts by weight of component (6) were formed into a premixture under high shear in order to

20 achieve good pigment dispersion (maximum particle size: Hegmann 5). The titanium dioxide was added slowly to assist wetting. Components (8) to (11) and the remainder of components (3) and (6) were added and mixed under high shear for 10 minutes.

25 The components (2), (4), (6), (7), (8), (9), (10) and (11) were obtained from the following manufacturers:

- 21 -

	2	Dispersing aid	Dispex 40	Allied Colloids
	4	Fungicide	Acticide SPX	Thor Industrial Biocides
5	6	Viscosity modifier	Rheovis CR2	Allied Colloids
	7	Defoamer	Foamex 1488	Tego Chemie Service
	8	Flow additives	Aerosol 0775	Cytec Industries
	9	Acrylic Emulsion	Xenacryl DP9B/1283	Baxenden Chemicals Ltd.
10	10	Blocked isocyanate	Obtained by reaction of HMDI trimer with DMPA and blocked with 3,5-dimethylpyrazole (see example 2)	
15	11	Coalescing solvent	Extrapro EEP	Eastman Chemical Ltd.

- 22 -

Example 4Coatings

The white paint composition of Example 3 was coated onto various substrates and stored at 120°C for 45 minutes. The resultant coatings were tested with the following results

Table 1

TEST	RESULT	TEST METHOD
Opacity	96%	R+D Method 22
Gloss 20° 60°	51% 82%	R+D Method 22
Reverse Impact: 1.8kg weight (1.0m)	PASSED	ASTM D2794-92 Steel Panels
Bend Test: Shim steel panels (3mm cylindrical mandrel)	PASSED	BS3900 Part E1
Cross cut adhesion: Substrate Smooth steel Matt steel Tin plate steel Aluminium Chrome treated aluminium	Rating 0 0 0 0 0	BS3900 Part E6 ISO 2409
Pencil Hardness Gouge Hardness Scratch Hardness	 3H 2H	ASTM D3363-92a
Weathering after 280 hours Gloss retention Observations on steel substrate	95% No rusting	ASTM G5388 4hrs UVB @ 60°C 4hrs condensation @ 50°C
Acetone resistance (double rubs)	>100 units	Standard

Unless otherwise stated, substrates were standard steel test panels.

- 23 -

Example 5 - Production of clear coat formulation

	<u>Component</u>	<u>Parts by weight</u>
1)	Xenacryl DP 9B/1345	54.1
2)	Blocked polyisocyanate	25.4
5	of Example 2	
3)	Tegowet KL 245	0.5
4)	Estasol	5.0
5)	Ectapro EEP	2.0
6)	Water	13.0

10 Method

(1) and (2) were added to a vessel and mixed well. (3), (4) and (5) were added and mixed thoroughly before adding (6).

Suppliers

- 15 1) Xenacryl DP9B/1345
Acrylic emulsion
Baxenden Chemicals
- 3) Tegowet KL245
Flow additive
- 20 Tego Chemie
- 4) Estasol
Coalescing solvent
Chemoxy International


- 24 -

CLAIMS

1. A water dispersible blocked polyisocyanate of formula (I)

5
$$R-Y_m \quad (I)$$

where R is an m valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group and comprising at least three consecutive ethylene oxide groups or at least one residue of a polyhydroxy carboxylic acid,
 10 and each group Y, which may be the same or different, is a group of formula (II)



15

where each R^1 is the same or different when n is more than 1 and each R^1 is an alkyl, alkenyl, aralkyl, N-substituted carbamyl, phenyl, NO_2 , halogen or a group —C(O)—O—R^2

20 where R^2 is hydrogen or an alkyl group;
 n is 0, 1, 2 or 3; and
 m is an integer of 2 or more.

2. A water dispersible mixture of blocked polyisocyanates each of the formula


25
$$R-Y_m$$

where the groups R are the same or different and each is an m valent group comprising an aliphatic, cycloaliphatic,

- 25 -

heterocyclic or aromatic group and wherein from 5 to 100 eq. wt% by weight groups comprise at least three consecutive ethylene oxide groups or at least one residue of a polyhydroxy carboxylic acid,

5 and each group Y, which may be the same or different, is a group of formula (II)



10

where the groups R^1 are the same or different when n is more than 1 and

each R_1 is an alkyl, alkenyl, aralkyl, N-substituted carbamyl, phenyl, NO_2 , halogen or a group —C(O)—O—R^2


15 where R^2 is hydrogen or an alkyl group;

n is 0, 1, 2 or 3; and


m is an integer of 2 or more.

3. A blocked polyisocyanate according to claim 1 or 2 wherein at least one group Y is

20




25




- 26 -

4. A blocked polyisocyanate according to claim 3 wherein at least one group Y is



5. A blocked polyisocyanate according to any one of the preceding claims wherein m is from 2 to 6.

10 6. A water dispersible product obtainable by
(a) contacting a polyisocyanate of formula (III)



wherein R^a is an q valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group and q is an
15 integer greater than 2

with an active hydrogen-containing compound bearing a hydrophilic group which is $-(CH_2CH_2O)_p-$ where p is 3 or more or with a polyhydroxy carboxylic acid group or derivative thereof to form a water dispersible polyisocyanate of
20 formula $R(NCO)_m$ wherein R is an m valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group, comprising at least three consecutive ethylene oxide groups or a residue of a polyhydroxy carboxylic acid; and


(b) blocking the water dispersible polyisocyanate
25 produced in step (a) with a pyrazole of formula (IV)



- 27 -

wherein each R^1 is the same or different when n is more than 1 and each R^1 is an alkyl, alkenyl, aralkyl, N-substituted carbamyl, phenyl, NO_2 , halogen or a group $-C(O)-O-R^2$ where R^2 is hydrogen or an alkyl group, n is 0, 1, 2 or 3; and m is an integer of 2 or more.

7. A process for producing a water dispersible blocked polyisocyanate as claimed in any one of the preceding claims which process comprises contacting a polyisocyanate of formula



wherein R is an m valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group and comprising at least three consecutive ethylene oxide groups or at least one residue of a polyhydroxy carboxylic acid and m is an integer of 2 or more with a pyrazole of formula (IV)




where each R^1 is the same or different when n is more than 1 and each R^1 is an alkyl, alkenyl, aralkyl, N-substituted carbamyl, phenyl, NO_2 , halogen or a group $-C(O)-O-R^2$ where R^2 is hydrogen or an alkyl group and n is 0, 1, 2 or 3 such that the reaction product contains no free isocyanate groups.

8. A process according to claim 7 which comprises the initial step of contacting a polyisocyanate of formula

- 28 -

(III)



wherein R^a is a q valent group comprising an aliphatic, cycloaliphatic, heterocyclic or aromatic group and q is an integer greater than 2 with an active hydrogen-containing compound bearing a hydrophilic group which is $-(CH_2CH_2O)_p-$ where p is 3 or more or a carboxylic acid group or derivative thereof to form a water dispersible polyisocyanate of formula $R(NCO)_m$.

9. An aqueous dispersion of at least one blocked polyisocyanate as claimed in any one of claims 1 to 6.

10. A coating composition which comprises a dispersion as claimed in claim 9 and a compound containing an active hydrogen.

11. A coating composition according to claim 10 which is a paint.

12. A coating composition according to claim 10 or claim 11 which comprises a pigment and a pigment carrier, wherein the pigment carrier is the compound containing an active hydrogen.

13. A composition according to any one of claims 10, 11 and 12 which contains 0.5 to 2 blocked isocyanate groups per active hydrogen containing group.

14. A method of coating a substrate which comprises applying a composition as claimed in any one of claims 10 to 13 to a substrate and then heating the deposited composition to crosslink the coating.

- 29 -

to 13 to a substrate and then heating the deposited composition to crosslink the coating.

15. A method according to claim 14 which additionally comprises the step of heating the coated substrate.

5 16. A method according to claim 14 or claim 15 wherein the composition is applied by electrodeposition.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 96/02440

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08G18/70 C08G18/80

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 576 952 (BAYER) 5 January 1994 see page 2, line 31 - page 5, line 15; claim 1	1
Y	--- WO,A,95 006 674 (OLIN) 9 March 1995 see page 3, line 12 - page 8, line 15; claims 1,5	1
A	--- EP,A,0 500 495 (CIBA-GEIGY) 26 August 1992 see page 3, line 27 - page 6, line 55; claim 1	1
A	--- WO,A,94 22935 (RHONE-POULENC) 13 October 1994 see page 2, line 1 - page 5, line 19; claim 1	1
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

12 December 1996

Date of mailing of the international search report

06 -01- 97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Bourgonje, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 96/02440

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,4 008 247 (TUCKER) 15 February 1977 see column 2, line 22 - column 14, line 11; claims 1-5	1
A	--- EP,A,0 159 117 (THE BAXENDEN CHEMICAL) 23 October 1985 cited in the application see the whole document -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 96/02440

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-576952	05-01-94	DE-A- 4221924 CA-A- 2099419 JP-A- 6056953 US-A- 5294665	13-01-94 04-01-94 01-03-94 15-03-94
WO-A-95006674		NONE	
EP-A-500495	26-08-92	CA-A- 2061526 JP-A- 5086164 US-A- 5210169	22-08-92 06-04-93 11-05-93
WO-A-9422935	13-10-94	FR-A- 2703358 FR-A- 2703357 AU-A- 6432494 BR-A- 9406135 EP-A- 0691993	07-10-94 07-10-94 24-10-94 27-02-96 17-01-96
US-A-4008247	15-02-77	US-A- 4101491 US-A- 4113958 US-A- 4190582 US-A- 4189601 US-A- 4191834 US-A- 4191833	18-07-78 12-09-78 26-02-80 19-02-80 04-03-80 04-03-80
EP-A-159117	23-10-85	DE-A- 3587024 US-A- 5352755 US-A- 4976837 US-A- 5246557	11-03-93 04-10-94 11-12-90 21-09-93